

LOCTITE EDAG 477SS RFU E&C

September 2014

PRODUCT DESCRIPTION

LOCTITE EDAG 477SS RFU E&C provides the following product characteristics:

Technology	Polyester
Appearance	Silver
Cure	Heat cure
Operating Temperature-continuous	121°C
Product Benefits	<ul style="list-style-type: none"> • Very low sheet resistance • Excellent abrasion resistance and hardness • Excellent flexibility • Extended screen residence time • Superior adhesion to polyester film • High Tg to prevent blocking
Application	Conductive Ink
Typical Assembly Applications	<ul style="list-style-type: none"> • Membrane switches • Flexible circuits • Printed circuit board

LOCTITE EDAG 477SS RFU E&C conductive, silver-based polymer thick film ink specifically designed for screen printing onto membrane switches.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	73.7
Percent Silver, %	65
Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP):	
Spindle 6, speed 20 rpm	14,000
Density, kg/l	2.5
Shelf Life @ 32 °C (from date of qualification in original seal), days	90
Flash Point, Tag Closed Cup Flash Tester, °C	99

TYPICAL SCREEN PRINTING PROCESS

This product is applied by standard screen printing techniques. The dried film thickness and final resistance is influenced by a number of factors, including screen mesh size, squeegee material, screen material, and emulsion thickness.

Recommended Thickness, dried, µm	8 to 13
Emulsion Thickness, Solvent resistant emulsion, µm	20 to 38
Screen Type:	
Monofilament polyester screen, mesh	157 to 280
Stainless steel screen, mesh	165 to 325
Squeegee (polyurethane or other solvent resistant material):	
For use on Polyester screens, durometer	60 to 70
For use on Stainless steel screens, durometer	70 to 80

TYPICAL CURING PERFORMANCE

LOCTITE EDAG 477SS RFU E&C can be cured at 200°F (93°C) and up. The higher the temperature, the lower the final resistance will be. Increasing the temperature will also reduce the time needed to achieve a final cure. For example, at 200°F (93°C) cure for 15 minutes; at 250°F (121°C) cure for 5 minutes.

Percent Volatiles

VOC, g/l 670

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Pencil hardness	B
Theoretical Coverage :	
sq ft/gal	556
m ² /kg	5.45

Electrical Properties

Sheet Resistance, ohms/sq	<0.02
---------------------------	-------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Mixing/Dilution

1. LOCTITE EDAG 477SS RFU E&C is supplied ready for use.
2. Should thinning become necessary, dilute 2% by weight with carbitol acetate.

Clean-up

1. The equipment can be cleaned with MEK, MIBK, Acetone or similar solvents.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

Optimal Storage : 32 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{psi} \times 145 = \text{N/mm}^2$$

$$\text{MPa} = \text{N/mm}^2$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose,**

arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1