

# LOCTITE EDAG 6038SS E&C

April 2020

## PRODUCT DESCRIPTION

LOCTITE EDAG 6038SS E&C provides the following product characteristics:

|                                    |   |
|------------------------------------|---|
| <b>Technology</b>                  | Thermoplastic   |
| Appearance                         | Silver  |
| Filler Type                        | Silver, Silver chloride blend   |
| Silver : Silver chloride Ratio     | 9 : 1   |
| <b>Cure</b>                        | Hot air drying  |
| Operating Temperature - Continuous | 100°C   |
| Product Benefits                   | <ul style="list-style-type: none"> <li>• Applicable with manual and semi-automatic</li> <li>• Compatible for use with Polycarbonate and polyester sheet and film</li> <li>• Non-critical, flexible low temperature drying cycles</li> <li>• Good flexibility</li> </ul> |
| <b>Application</b>                 | Conductive Ink  |
| Typical Medical Device Application | ECG disposable electrodes and Bio medical sensors   |

LOCTITE EDAG 6038SS E&C conductive, screen printable ink consist of very finely divided silver and silver chloride particles in a blend of thermoplastic resins. It is specially designed for use as an electrode material in bio medical sensing devices.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

|   |        |
|---|--------|
| Solids Content, %   | 66     |
| Viscosity, Brookfield , 20 °C, mPa·s (cP):                                    |        |
| Speed 20 rpm  | 20,000 |
| Density, Kg/m <sup>3</sup>  | 1,970  |
| Shelf Life @ 8 to 28°C, days<br>(from date of qualification in original seal) | 365    |
| Coverage , m <sup>2</sup> /kg:  |        |
| Wet product @ 10 µm dry coating thickness                                     | 17     |
| Flash Point , °C  | 62     |

## TYPICAL SCREEN PRINTING PROCESS

|   |           |
|---|-----------|
| <b>• Printing Equipment Type</b>          |           |
| Manual                                    |           |
| Semi-automatic                            |           |
| <b>• Recommended Screen Type</b>          |           |
| Monofilament polyester screen, threads/cm | 68 to 110 |
| <b>• Recommended Squeegee</b>             |           |
| Polyurethane , durometer                  | 70 to 75  |
| <b>• Emulsion Thickness</b>               |           |
| Emulsion Thickness , µm                   | 20 to 40  |

## • Applied Dry Coating Thickness

Applied Dry Coating Thickness, µm 7 to 12

## TYPICAL DRYING CYCLE

### Recommended Drying Cycle

Conventional Air Circulated Oven:  
 30 minutes @ 80°C or  
 15 minutes @ 95°C or  
 15 minutes @ 120°C

LOCTITE EDAG 6038SS E&C can be dried immediately, after printing, at temperatures between 70 to 120°C.

Use jet air and infra-red drying for high speed production.

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

Dry Coating on polycarbonate film dried 15 minutes @ 120°C

### Physical Properties

Adhesion, ASTM 3359, grade 5B

### Electrical Properties

Sheet Resistance@ 25µm dry coating thickness, ≤0.04 ohms/sq

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

## DIRECTIONS FOR USE

1. LOCTITE EDAG 6038SS E&C is supplied ready for use and does not require dilution.
2. Stir LOCTITE EDAG 6038SS E&C prior to each use.
3. Avoid rapid stirring as this causes air entrapment.
4. If dilution is necessary, use Arcosolv PM-Acetate, (1 to 2% by weight).
5. If a gel structure forms after extended storage, the product may be warmed slightly in a water bath (not exceeding 50°C) and stirred.

## CLEAN-UP

1. The equipment can be cleaned with MEK, MIBK, Acetone or similar solvents.

## STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

**Optimal Storage : 8 to 28 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$

$\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$

$\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$

$\text{mPa} \cdot \text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned

herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference **N/A**