

8327GL6



Non-Silicone Liquid Thermal Gel

8327GL6 is a 1-part, silicone-free, paste-like gel offering extreme thermal conductivity and flame retardancy. This form-in-place, non-curable gel is easy to dispense and conforms to the component/heatsink interface, ensuring all air is displaced and eliminating hotspots. Its low modulus and robust temperature range allows for high heat dissipation, low component stress and thermal cycling stability. Circuits can be powered up immediately following application, offering exceptional convenience.

It is most often used as a gap filler on heatsinks to CPUs, LEDs, and other electronic components. Its high thermal conductivity makes it ideal for energy-intensive devices like telecommunications equipment, PCs for gamers and electric vehicle battery packs.

Features & Benefits

- Extreme thermal conductivity
- Flame retardant—meets UL94 V-0
- 1-part, non-curable, dispensable gel
- Zero pump out—no slump under low pressure
- Silicone-free, will not contaminate surfaces
- Low modulus, ideal for aggressive thermal cycling conditions



Available Packaging

Part #	Packaging	Net Wt.
8327GL6-25ML	Jar	54 g
8327GL6-30ML	Cartridge	66 g
8327GL6-180ML	Cartridge	294

Storage and Handling

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS). To maximize shelf life, recap product firmly when not in use.

Properties

Color	Grey	—
Density	2.3 g/mL	Hydrostatic Weighing
Service Temperature Range	-40–120 °C	—
Intermittent Temperature	150 °C	—
Resistivity	10 ⁹ Ω·cm	ASTM D257
Dissipation Factor @ 1 kHz	0.005	—
Breakdown Voltage @ 1 mm	3 200 V	—
Thermal Conductivity @ 25 °C	6.0 W/(m·K)	ASTM E1461
Flow Rate @ 90 psi, 0.1" orifice	4–6 g/min	—
Bond Line Thickness	<25 μm	—
Viscosity @ 25 °C	7 000 Pa·s	Brookfield Engineering labs Inc. IPCTM-65- Method 2.4.24.4
Shelf Life	2 y	—

Disclaimer: This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

MG Chemicals 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6 ISO 9001:2015 Quality Management System SAI Global File: 004008
support@mgchemicals.com North America +(1) 800-340-0772 International +(1) 905-331-1396 Europe +44 1663 362888 30 September 2025 / Ver. 2.0